

ORIGINAL
ARTICLE

Received 2025-05-30

Revised 2025-08-08

Accepted 2025-10-18

Comparative Effects of Different Surface Treatments on Shear Bond Strength of Metal Brackets Bonded to Eroded Enamel: An in Vitro Study

Milad Soleimani ¹, Hengameh Banaei ², Manijeh Mohammadian ³ ✉¹ Department of Orthodontics, School of Dentistry, Shahid Beheshti University of Medical Sciences, Tehran, Iran² Student Research Committee, Alborz University of Medical Sciences, Karaj, Iran³ Department of Dental Biomaterials, School of Dentistry, Iran University of Medical Sciences, Tehran, Iran

Abstract

Background: This study aimed to compare the effects of different surface treatments on shear bond strength (SBS) of metal brackets to eroded enamel. **Materials and Methods:** In this in vitro study, 76 extracted premolars were immersed in Coca-Cola 4 times, each time for 2 minutes to cause enamel erosion. They were then randomly assigned to 4 groups (n=19) for surface treatment by acid etching (control), bur grinding plus acid etching, sandblasting plus acid etching, and erbium-doped yttrium aluminum garnet (Er:YAG) laser irradiation plus acid etching. Metal brackets were then bonded to the buccal surface of the teeth and after thermocycling, their SBS was measured in a universal testing machine. After debonding, the adhesive remnant index (ARI) score was determined under a stereomicroscope. SBS of higher than 6 was considered as optimal (Reynolds threshold). **Results:** The control group showed the highest, and the laser group showed the lowest SBS; however, the difference in SBS was not statistically significant among the four groups (P=0.35). Acid etching group had 2 cases of failure in SBS values, while other groups had none. The study groups had no significant difference in the ARI scores either (P=0.82); nonetheless, sandblasting and laser groups had the highest frequency of ARI score 3 (all adhesive remaining on the surface). **Conclusion:** Bur grinding, sandblasting, and Er:YAG laser irradiation did not significantly change the SBS of metal brackets to eroded enamel compared with acid etching alone, and all the tested methods yielded acceptable SBS values. [GMJ.2025;14:e3951] DOI:[10.31661/gmj.v14iSP1.3951](https://doi.org/10.31661/gmj.v14iSP1.3951)

Keywords: Lasers; Solid-State; Orthodontic Brackets; Shear Strength; Tooth Erosion

Introduction

In orthodontic treatment, brackets are bonded to the enamel surface. However, the enamel surface is not sound and intact in all cases, and may be hypoplastic, eroded, or fluorosed, making it difficult to achieve an optimal bracket bond strength [1]. Among these conditions, enamel erosion poses a significant

challenge due to its impact on the enamel's integrity. Enamel erosion is defined as irreversible demineralization of the enamel surface due to the effect of acidic chemical agents. Normally, exposure of enamel to acidic agents results in its temporary demineralization, and the buffering capacity of the saliva changes the pH of the oral environment and remineralizes the enamel surface [2, 3]. However, if

GMJ

Copyright© 2025, Galen Medical Journal.
This is an open-access article distributed
under the terms of the Creative Commons
Attribution 4.0 International License
(<http://creativecommons.org/licenses/by/4.0/>)
Email:gmj@salviapub.com

✉ **Correspondence to:**

Manijeh Mohammadian, Department of Dental Biomaterials, School of Dentistry, Iran University of Medical Sciences, Tehran, Iran.

Telephone Number: +98 21 8670 2030

Email Address: dr.mohamadian77@gmail.com

the acidity exceeds the buffering capacity of the saliva (due to high frequency of exposures or excessively low pH), remineralization does not occur, and the enamel remains irreversibly demineralized [2, 3]. Approximately 30% of the population suffer from dental erosion [4, 5]. Xerostomia, aging, and poor socioeconomic status contribute to dental erosion [6]. Eroded enamel is more susceptible to mechanical stress since it has lost a portion of its mineral content due to acid exposure. Resultantly, brackets often have a lower bond strength to eroded enamel compared with sound enamel [5, 7-10].

By the increasing demand for orthodontic treatment among adults, and increased prevalence of dental erosion with age, bracket bonding to eroded enamel has become a challenge for orthodontists [4, 5]. Therefore, researchers have been in search of strategies to increase the shear bond strength (SBS) of brackets to eroded enamel. It has been reported that acid etching of an eroded enamel surface alone for bracket bonding decreases the enamel microhardness and strength. Therefore, surface treatments such as sandblasting [9], application of sodium calcium silicate [5], TiF₄ varnish [8], or casein phosphopeptide amorphous calcium fluoride paste, CO₂ laser irradiation [10], and bur grinding have been suggested to increase the microhardness of the eroded enamel, and subsequently enhance bracket SBS. Sandblasting, bur grinding, and laser irradiation increase enamel porosities and surface roughness, which are believed to increase adhesive penetration, and improve the bond strength [11].

Considering the lower microhardness of eroded enamel compared with sound enamel [5, 7-10], and the challenges encountered in bracket bonding to eroded enamel, this study aimed to compare the effects of different surface treatments including acid etching, bur grinding, sandblasting, and erbium-doped yttrium aluminum garnet (Er:YAG) laser irradiation on SBS of metal brackets to eroded enamel. The null hypothesis of the study was that no significant difference would be found among the aforementioned four surface treatments with respect to their effect on SBS of metal brackets to eroded enamel.

Materials and Methods

This *in vitro* experimental study was conducted on 76 sound human premolars with no caries, restoration, enamel hypomineralization, cracks, or fluorosis in their buccal surface that had been extracted for orthodontic reasons. The study protocol was approved by the ethics committee of the university (IR.ABZUMS.REC.1401.121).

Sample Size

The sample size was calculated to be 19 in each group according to studies by Farhadifard *et al.*, [12] and Najafi *et al.*, [13] assuming 95% confidence interval and study power of 80% using G Power software.

Specimen Preparation

The teeth were cleaned by a scalpel and a toothbrush, and were stored in saline at room temperature until the experiment. They were




Figure 1. ARI scores; (A) score 0 (no adhesive remaining on the enamel surface), (B) score 1 (less than 50% of adhesive remaining on the enamel surface), (C) score 2 (more than 50% of adhesive remaining on the enamel surface), (D) score 3 (all adhesive remaining on the enamel surface)

immersed in 0.5% chloramine T solution one week prior to the onset of the erosion process. To induce enamel erosion, the teeth were immersed in 500 mL of Coca-Cola solution with a pH of 2.3 at room temperature for 2 minutes [7, 8, 10, 14-16] and were then rinsed with water for 10 seconds. This process was repeated 3 times with fresh Coca-Cola solution. In other words, all teeth were immersed in Coca-Cola solution for a total of 8 minutes [10, 14]. After completion of the erosive cycle, the specimens were stored in saline.

Prior to surface treatments, the buccal surface of all teeth was cleaned by a rubber cup. The teeth were then randomly assigned to 4 groups (n=19) for the following surface treatments [12]:

Group 1 (control): Acid etching alone: The buccal surface of the teeth was etched with 37% phosphoric acid (Etchant-37; Denfil, Korea) for 15 seconds, and then rinsed with water for 30 seconds.

Group 2: Bur grinding: The buccal surface of the teeth was ground by a tapered diamond bur with 1.2 mm diameter and 8 mm length with highspeed handpiece in two perpendicular directions under water spray.

Group 3: Sandblasting: The buccal surface of the teeth was sandblasted with 50 µm aluminum oxide particles with 65 psi pressure at 10 mm distance for 7 seconds using a sandblaster (Fineblast; Kpushafan Pars, China).

Group 4: The buccal surface of the teeth was subjected to Er:YAG laser irradiation (Fotona, China) with a SN614 laser handpiece with 2940 nm wavelength, 1.5 W power, 100 mJ energy density, 300 femtosecond pulse width and 15 Hz frequency in pulse mode [17]. The distance between the handpiece tip and the buccal surface of the teeth was 1 mm, and a cylindrical tip with 1.3 mm diameter was used. The air/water flow rate was 4 mL/s.

The teeth in groups 2-4 were then etched with

37% phosphoric acid as explained for group 1.

After the surface treatments, metal brackets (022 slot MBT American Orthodontics) were bonded to the buccal surface of the teeth using GC Ortho light-cure orthodontic adhesive (GC, Japan). For this purpose, the tooth surface and brackets were completely dried, composite was applied over the bracket base, and the bracket was positioned at the center of the buccal surface of the tooth. The bracket position was adjusted by using a dental explorer, and excess composite was removed. Composite curing was performed using a LED curing unit (Guilin woodpecker medical instrument Co., Ltd., Germany) in ortho mode. Light was irradiated directly to the brackets for 10 seconds, followed by 10 seconds of irradiation of the composite at the bracket-tooth interface from the left side, and 10 seconds from the right side. The specimens were then stored in saline.

Thermocycling and SBS Testing

To better simulate the intraoral environment, the tooth-bracket assemblies underwent thermocycling for 3000 cycles in a thermocycler (TC300; Vafaei Industrial, Tehran, Iran) between 5-55°C with a dwell time of 20 seconds and a transfer time of 10 seconds [18]. After 48 hours, the specimens were mounted in auto-polymerizing acrylic resin (Acropars, Iran), and the SBS of brackets to the eroded enamel was measured in a universal testing machine (Zwick Roell, Ulm, Germany). Vertical load was applied to the enamel-bracket interface by a flat-end stainless steel blade parallel to the longitudinal tooth axis at a crosshead speed of 1 mm/minute until bracket debonding. To calculate the SBS in megapascals (MPa), the load required for bracket debonding in Newtons (N) was divided by the bracket base surface area in square-millime-

Table 1. Measures of central dispersion for the SBS (MPa) of metal brackets to eroded enamel

Group	Mean	SD	Minimum	Maximum	P-value
Acid etching	21.77	10.7	5.93	47.14	0.35
Bur grinding	18.46	6.6	4.13	28.07	
Sandblasting	18.17	8	7.97	36.05	
Er:YAG laser	17.44	5.72	11.13	31.92	

ters (mm²). The length and width of brackets were initially measured by a caliper to be 3.7 mm and 2.9 mm, respectively. Accordingly, the bracket base surface area was calculated.

Determination of Adhesive Remnant Index (ARI) Score

After bracket debonding, the buccal surface of the teeth was inspected under a stereomicroscope (SMZ800, Nikon, Japan) at x10 magnification, and the ARI score was determined according to Artun and Bergland [16] as follows (Figure-1): Score 0 indicates no adhesive remaining on the enamel surface; Score 1 indicates less than 50% of adhesive remaining on the enamel surface; Score 2 indicates more than 50% of adhesive remaining on the enamel surface; and Score 3 indicates all adhesive remaining on the enamel surface.

Statistical Analysis

Based on the Reynolds, I. R. (1975) study [17], optimal value for SBS in samples enamel bonding is 6 to 8 MPa. We considered SBS lower than 6 as non-optimal. Normal distribution of data was confirmed by the Shapiro-Wilk test ($P > 0.05$). Thus, comparisons were made by one-way ANOVA followed by pairwise comparisons with the Dunnett post hoc test. All statistical analyses were performed using SPSS version 26 (SPSS Inc., IL, USA) at 0.05 level of significance.

Results

SBS

The SBS values, measured in megapascals (MPa), were assessed to determine the bonding effectiveness of metal brackets to eroded enamel surfaces after different surface treatments. The mean SBS values for the groups were as follows: acid etching (21.77 ± 10.7 MPa), bur grinding (18.46 ± 6.6 MPa), sandblasting (18.17 ± 8.0 MPa), and Er:YAG laser irradiation (17.44 ± 5.72 MPa). The acid

etching group exhibited the highest mean SBS, while the Er:YAG laser group showed the lowest.

The standard deviations indicate variability within each group, with the acid etching group showing the highest dispersion ($SD=10.7$ MPa) and the Er:YAG laser group the lowest ($SD=5.72$ MPa). The minimum and maximum SBS values further highlight the range of bonding strengths, with acid etching ranging from 5.93 to 47.14 MPa, bur grinding from 4.13 to 28.07 MPa, sandblasting from 7.97 to 36.05 MPa, and Er:YAG laser from 11.13 to 31.92 MPa.

Statistical analysis using one-way ANOVA revealed no significant differences in SBS among the four groups ($P=0.35$).

As shown in Table-2, a chi-square test of independence was conducted to examine the association between SBS optimal status (Optimal: $SBS \geq 6$ MPa; Non-optimal: $SBS < 6$ MPa) and treatment groups. The test revealed no significant association between SBS optimal status and treatment group, $\chi^2 (3, N=76) = 6.16, P=.10$, suggesting that the distribution of optimal and non-optimal SBS values does not significantly differ across the groups.

ARI Score

The frequency distribution of ARI scores (Table-3), which indicate the amount of adhesive remaining on the enamel surface after bracket debonding, was analyzed across the four groups, and the results were statistically non-significant ($P=0.82$).

In the acid etching group, the most frequent ARI score was 3 (26.3%, $n=5$), indicating that all adhesive remained on the enamel surface in these cases. This group also had 8.36% ($n=7$) with an ARI score of 0 (no adhesive remaining), 21.1% ($n=4$) with a score of 1 (less than 50% adhesive remaining), and 15.8% ($n=3$) with a score of 2 (more than 50% adhesive remaining). The bur grinding group showed an even distribution for ARI scores

Table 2. Frequency Distribution of SBS Optimal Status Across Treatment Groups Optimal Status

Optimal Status	Acid etching	Bur grinding	Er:YAG laser	Sandblasting
Non-optimal	2 (10.5%)	0 (0.0%)	0 (0.0%)	0 (0.0%)
Optimal	17 (89.5%)	19 (100.0%)	19 (100.0%)	19 (100.0%)

0, 1, and 3 (26.3% each, n=5), with 21.1% (n=4) for a score of 2. The sandblasting group had the highest frequency of ARI score 3 (47.4%, n=9), followed by equal frequencies for scores 0 and 1 (21.1% each, n=4), and the lowest frequency for score 2 (10.5%, n=2). Similarly, the Er:YAG laser group also had the highest frequency at ARI score 3 (47.4%, n=9), followed by score 1 (26.3%, n=5), and equal frequencies for scores 0 and 2 (15.8% and 10.5%, respectively, n=3 and n=2).

Discussion

In our study, SBS values compared among groups, was not successful in determining most effective surface treatment for bonding metal brackets to eroded enamel. Sandblasting yielded the lowest SBS, indicating it may not be suitable for achieving reliable bond strength in this context. The high variability in the Er:YAG laser group suggests that its effectiveness may depend on specific parameters or operator technique, warranting further investigation. The ARI score distributions showed no significant differences among groups, with a trend toward higher adhesive retention on the enamel surface (ARI score 3) in the sandblasting and laser groups.

Er:YAG laser was used in the laser group in the present study, which is the most commonly used laser type for dental hard tissue ablation. It is mainly absorbed by water; however, it has sufficient energy density to cause photoacoustic effects and cavitation with minimal thermal damage [18]. Laser irradiation

changes the physical and chemical properties of the enamel, and roughens the surface. It eliminates the prismless enamel from the tooth surface and exposes the enamel rods for adhesive bonding. The laser group showed the lowest SBS in the present study; however, it had no significant difference in SBS with other groups. This finding may be due to the fact that although laser irradiation increases the surface roughness, the created porosities on the surface are irregular and do not follow a homogenous pattern [19]. Laser irradiation creates cup-shaped depressions with no undercut, which cannot provide optimal mechanical retention; while, acid etching creates regular undercuts that result in formation of homogenous resin tags that increase the bond strength [19]. Also, thermal degeneration of collagen fibers caused by laser irradiation can decrease the bond strength to enamel, although enamel has only 0.5% collagen [20]. The present result in this regard was in line with the findings of Sallam and Arnout [21]. They showed that Er:YAG laser irradiation with 2940 nm wavelength, 1.5 W power, and 15 Hz frequency had no significant effect on SBS of brackets. Çokaçoğlu *et al.* [22] reported similar results as well; however, they showed that Er:YAG laser irradiation increased the SBS when a 2-step self-etch adhesive was applied. A total-etch system was used for bonding of brackets to eroded enamel in the present study. The same results were reported by Lopes *et al* [23]. However, in contrast to the present results, Kiryk *et al.* [24] reported that Er:YAG laser irradiation of enamel surface followed by acid

Table 3. Frequency Distribution of Different ARI Scores

ARI score		Acid etching	Bur grinding	Sandblasting	Laser irradiation
0	Number	7	5	4	3
	Percentage	8.36	26.3	21.1	15.8
1	Number	4	5	4	5
	Percentage	21.1	26.3	21.1	26.3
2	Number	3	4	2	2
	Percentage	15.8	21.1	10.5	10.5
3	Number	5	5	9	9
	Percentage	26.3	26.3	47.4	47.4

etching significantly increased the SBS of brackets to sound enamel. Difference between their results and the present findings may be due to the fact that they evaluated bonding to sound enamel; whereas, eroded enamel was evaluated in the present study. Also, the laser parameters were different in the two studies. Different results were also reported by Najafi *et al.*, [14] who showed that Er:YAG laser irradiation and acid-etching of bleached and desensitized enamel significantly increased the SBS to metal brackets. Difference between their results and the present findings may be due to evaluation of different types of enamel (bleached versus eroded enamel) and different laser parameters.

Bur grinding was also performed in the present study, which did not significantly change the SBS compared with other groups. Grinding eliminates the prismless enamel, which has lower potential for bonding, and exposes the enamel with higher bonding potential [25]. Enamel removal with grinding is minimal and limited to the 30- μ m prismless enamel. It does not damage the tooth surface. The present results regarding no significant effect of bur grinding on SBS were in line with the findings of Najafi *et al.*, [10] who found no significant difference between grinding and laser irradiation. However, grinding yielded a higher SBS than acid etching, and lower SBS than sandblasting in their study, which was different from the present results. Also, Farhadifard *et al.* [9] reported that grinding increased the SBS of old composite to ceramic brackets. Their results were different from the present findings due to evaluation of different bracket types, substrates, and adhesives. Moreover, the grinding parameters were not the same in the two studies.

In the present study, sandblasting could not significantly change the SBS compared with other groups. This result can be due to dispersion of alumina particles in the porous surface, preventing optimal penetration of adhesive into the porosities. Resultantly, the sandblasted surface cannot enhance the bond strength [26]. Also, sandblasting may roughen a surface larger than the bracket bonding area, which is another drawback [26]. Sandblasting increases the surface roughness and the available surface area for bonding [26]. The

present result regarding sandblasting was in line with the findings of Oskoei *et al.*, [27] although they compared Er,Cr:YSGG laser and sandblasting for enhancement of SBS of stainless-steel brackets to amalgam surfaces. Similarly, Lopes *et al.* [23] found no significant difference between Nd:YAG laser and sandblasting for enhancement of SBS of brackets to sound enamel. Nonetheless, Frhadifard *et al.* [9] reported that sandblasting significantly increased the SBS of ceramic brackets to old composite, which can be due to differences in bracket type, dental substrate, adhesive type, and sandblasting parameters between the two studies. Also, Najafi *et al.* [10] reported that sandblasting significantly increased the SBS of metal brackets to old composite. Difference between their results and the present findings can be attributed to evaluation of different bonding substrates.

In the present study, acid etching alone yielded the highest SBS, although it had no significant difference with SBS in other groups. Acid etching irregularly changes the enamel surface, and increases the surface free energy. Application of a resin-based liquid over this surface results in resin penetration into the surface irregularities and micro-mechanical interlocking following polymerization. The resin micro-tags formed within the enamel surface are the main mechanism of resin adhesion to the enamel [8]. The present results regarding the SBS of the acid-etched group were similar to the findings of de Vasconcelos Leão *et al.*, [6]; nonetheless, Najafi *et al.* [10] reported that the acid-etched group yielded the lowest SBS, which was in contrast to the present findings. This difference may be explained by the difference in the type of substrate (eroded enamel in the present study versus old composite in their study).

Assessment of ARI scores revealed no significant difference among the four groups in the present study. Ideally, debonding should occur at the adhesive-bracket interface, and the outermost enamel surface should remain intact. Debonding at the adhesive-bracket interface minimizes the risk of enamel damage, and is therefore preferred by most orthodontists. However, debonding at the adhesive-bracket interface leaves higher amounts of residual adhesive on the enamel surface, which should

be eliminated by bur. Debonding at the enamel-adhesive interface may damage the enamel surface, and is not favored by orthodontists [28]. An ARI score 0 indicates poor bonding at the enamel-adhesive interface while a score 3 indicates a strong bond at the enamel-adhesive interface [29]. Although the present results showed no significant difference among the four groups in the ARI scores, sandblasted and laser-irradiated groups showed the highest frequency of ARI score 3.

The current results were in agreement with the findings of Najafi *et al.*, [10] who showed no significant effect of CO₂ laser irradiation of old composite on ARI score after metal bracket debonding. However, grinding and sandblasting increased the ARI score in their study, which was different from the present results. Different results were also reported by de Vasconcelos Leão *et al.*, [6] who demonstrated that sandblasting (75 psi, 4 seconds, 10 mm distance) resulted in a higher ARI score compared with the non-sandblasted control group. Difference in the results may be attributed to different sandblasting parameters. Also, the adopted technique for induction of enamel erosion was different in the two studies. Moreover, the acid-etched control group in their study did not undergo erosion, which was different from the methodology of the present study. Furthermore, different adhesive types were used in the two studies. Nonetheless, it should be noted that the ARI is a subjective index, and experience and expertise of the clinicians can affect their judgment. This factor may also explain variations in the re-

ported results in the literature [16]. Differences in the morphology of brackets, interfacial properties of the bracket-adhesive assembly, and thickness of the adhesive layer, which is influenced by the bracket base design, can also affect the results [30].

This study had some limitations. Despite the conduction of thermocycling, clinical environment cannot be perfectly simulated *in vitro*, which limits the generalizability of the findings. Also, only one type of laser with certain exposure parameters was used in the present study. Future studies are required on different laser types with various parameters, and also on sandblasting with different parameters in terms of particle size and pressure. Also, other adhesive systems and non-metal brackets should be assessed in future studies. Furthermore, changes in the enamel surface and hardness after erosion and surface treatments should be further evaluated. Finally, clinical studies are required to obtain more reliable results.

Conclusion

Bur grinding, sandblasting, and Er:YAG laser irradiation did not significantly change the SBS of metal brackets to eroded enamel compared with acid etching alone, and all the tested methods yielded acceptable SBS values.

Conflict of Interest

The author declares that they have no competing interests.

References

1. Koletsi D, Gerald Bradley T, Kavvadia K. Bonding and Debonding Considerations in Orthodontic Patients Presenting Enamel Structural Defects. *Debonding and Fixed Retention in Orthodontics: An EvidenceBased Clinical Guide*. 2023 Sep 5:4362.
2. Enax J, Fandrich P, Schulze zur Wiesche E, Epple M. The remineralization of enamel from saliva: A chemical perspective. *Dentistry Journal*. 2024 Oct 23;12(11):339.
3. Hicks J, GarciaGodoy F, Flaitz C. Biological factors in dental caries: role of saliva and dental plaque in the dynamic process of demineralization and remineralization (part 1). *Journal of Clinical Pediatric Dentistry*. 2004 Sep 1;28(1):4752.
4. YanFang Ren D. Dental erosion: etiology, diagnosis and prevention. *ADA: The academy of dental therapeutic and stomatology*. 2011;2011:7684.
5. Costenoble A, Vennat E, Attal JP, Dursun E. Bond strength and interfacial morphology of orthodontic brackets bonded to eroded enamel treated with calcium silicatesodium phosphate salts or resin infiltration. *Angle*

- Orthod. 2016;86(6):90916.
6. Skalsky Jarkander M, Grindefjord M, Carlstedt K. Dental erosion, prevalence and risk factors among a group of adolescents in Stockholm County. *Eur Arch Paediatr Dent.* 2018;19(1):2331.
 7. Jordão MC, Forti GM, Navarro RS, Freitas PM, Honório HM, Rios D. CO₂ laser and/or fluoride enamel treatment against in situ/ex vivo erosive challenge. *J Appl Oral Sci.* 2016;24(3):2238.
 8. Medeiros MID, Carlo HL, Santos RLD, Sousa FB, Castro RD, França RCS et al. TiF₄ varnish protects the retention of brackets to enamel after in vitro mild erosive challenge. *J Appl Oral Sci.* 2018;26:e20170222.
 9. de Vasconcelos Leão L, Oliveira A, Moreira JC, Paranhos LR, de Mello Rode S, Nahsan FPS. The effect of aluminum oxide sandblasting and discs on shear bond strength of metal brackets rebonded in eroded enamel. *Research, Society and Development.* 2021;10(13):e34101320132e.
 10. Kasraei S, Kasraei P, Valizadeh S, Azarsina M. Rehardening of Eroded Enamel with CPPACFP Paste and CO₂(2) Laser Treatment. *Biomed Res Int.* 2021;2021:3304553.
 11. Zhu JJ, Tang AT, Matinlinna JP, Hägg U. Acid etching of human enamel in clinical applications: a systematic review. *J Prosthet Dent.* 2014;112(2):12235.
 12. Farhadifard H, RezaeiSoufi L, Farhadian M, Shokouhi P. Effect of different surface treatments on shear bond strength of ceramic brackets to old composite. *Biomater Res.* 2020;24(1):20.
 13. Zarif Najafi H, Mousavi M, Nouri N, Torkan S. Evaluation of the effect of different surface conditioning methods on shear bond strength of metal brackets bonded to aged composite restorations. *Int Orthod.* 2019;17(1):808.
 14. Tantbirojn D, Huang A, Ericson MD, Poolthong S. Change in surface hardness of enamel by a cola drink and a CPPACP paste. *J Dent.* 2008;36(1):749.
 15. Kato MT, Magalhães AC, Rios D, Hannas AR, Attin T, Buzalaf MA. Protective effect of green tea on dentin erosion and abrasion. *J Appl Oral Sci.* 2009;17(6):5604.
 16. Reynolds IR. A review of direct orthodontic bonding. *British journal of orthodontics.* 1975 Jul 1;2(3):1718.
 17. de Oliveira DSB, Santin GC, Honório HM, Rios D, Gatón PH, da Silva LAB et al. Single application of casein phosphopeptideamorphous calcium phosphate pastebased paste prevents in vitro erosive wear. *European Journal of General Dentistry.* 2016;5(02):6973.
 18. Zarif Najafi H, Bagheri R, Pakshir HR, Tavakkoli MA, Torkan S. Effect of different surface treatment on the shear bond strength of metal brackets to bleached and desensitized enamel. *Int Orthod.* 2019;17(1):739.
 19. Artun J, Bergland S. Clinical trials with crystal growth conditioning as an alternative to acidetch enamel pretreatment. *Am J Orthod.* 1984;85(4):33340.
 20. Ozer T, Başaran G, Berk N. Laser etching of enamel for orthodontic bonding. *Am J Orthod Dentofacial Orthop.* 2008;134(2):1937.
 21. Dunn WJ, Davis JT, Bush AC. Shear bond strength and SEM evaluation of composite bonded to Er:YAG laserprepared dentin and enamel. *Dent Mater.* 2005;21(7):61624.
 22. Gutknecht N, Apel C, Schäfer C, Lampert F. Microleakage of composite fillings in Er,Cr:YSGG laserprepared class II cavities. *Lasers Surg Med.* 2001;28(4):3714.
 23. EstevesOliveira M, Zezell DM, Apel C, Turbino ML, Aranha AC, Eduardo Cde P et al. Bond strength of selfetching primer to bur cut, Er,Cr:YSGG, and Er:YAG lased dental surfaces. *Photomed Laser Surg.* 2007;25(5):37380.
 24. Sallam RA, Arnout EA. Effect of Er:YAG laser etching on shear bond strength of orthodontic bracket. *Saudi Med J.* 2018;39(9):9227.
 25. Çokakoğlu S, Nalçacı R, Üşümez S, Malkoç S. Effects of Different Combinations of Er:YAG LaserAdhesives on Enamel Demineralization and Bracket Bond Strength. *Photomed Laser Surg.* 2016;34(4):16470.
 26. Lopes MS, Pereira DL, de Oliveira Mota CCB, Amaral MM, Zezell DM, Gomes ASL. The lingual enamel morphology and bracket shear bond strength influenced by Nd:YAG laser and aluminum oxide sandblasting preconditioning. *Clin Oral Investig.* 2021;25(3):11518.
 27. Kiryk J, Matys J, Nikodem A, Burzynska K, GrzechLesniak K, Dominiak M et al. The Effect of Er:YAG Laser on a Shear Bond Strength Value of Orthodontic Brackets to EnamelA Preliminary Study. *Materials (Basel).* 2021;14(9): 2093.
 28. Halwai HK, Kamble RH, Hazarey PV, Gautam V. Evaluation and comparison of the shear bond strength of rebonded orthodontic brackets with air abrasion, flaming, and

- grinding techniques: an in vitro study. *Orthodontics (Chic)*. 2012;13(1):e19.
29. Baumgartner S, Koletsi D, Verna C, Eliades T. The Effect of Enamel Sandblasting on Enhancing Bond Strength of Orthodontic Brackets: A Systematic Review and Metaanalysis. *J Adhes Dent*. 2017;19(6):46373.
30. Oskoe PA, Kachoei M, Rikhtegaran S, Fathalizadeh F, Navimipour EJ. Effect of surface treatment with sandblasting and Er,Cr:YSGG laser on bonding of stainless steel orthodontic brackets to silver amalgam. *Med Oral Patol Oral Cir Bucal*. 2012;17(2):e2926.